US005580508A

United States Patent [19]

Kobayashi et al.

[11] **Patent Number: 5,580,508**

[45] **Date of Patent: Dec. 3, 1996**

[54] **PROCESS FOR PREPARING CALCIUM SILICATE ARTICLES**

[75] Inventors: **Waichi Kobayashi**; **Satoshi Otaka**; **Hideo Uchiyama**; **Toshihiro Nakata**; **Tetsuya Sadatani**, all of Ube, Japan

[73] Assignee: **Ube Industries, Ltd.**, Yamaguchi, Japan

[21] Appl. No.: **395,159**

[22] Filed: **Feb. 27, 1995**

Related U.S. Application Data

[63] Continuation of Ser. No. 217,630, Mar. 24, 1994, abandoned, which is a continuation of Ser. No. 899,047, Jun. 16, 1992, abandoned, which is a continuation of Ser. No. 771,796, Oct. 4, 1991, abandoned, which is a continuation of Ser. No. 530,426, May 29, 1990, abandoned, which is a continuation of Ser. No. 253,057, Oct. 4, 1988, abandoned, which is a continuation-in-part of Ser. No. 145,647, Jan. 13, 1988, abandoned, which is a continuation of Ser. No. 35,077, Apr. 6, 1987, abandoned.

[30] **Foreign Application Priority Data**

Apr. 4, 1986 [JP] Japan 61-76701
Nov. 7, 1986 [JP] Japan 61-263651

[51] **Int. Cl.**[6] **B29C 71/00**

[52] **U.S. Cl.** **264/234**; 264/294; 264/345

[58] **Field of Search** 264/234, 333, 264/345, 294

[56] **References Cited**

U.S. PATENT DOCUMENTS

3,901,991	8/1975	Ueda et al.	428/446
3,957,522	5/1976	Matsuo et al.	106/109
4,146,402	3/1979	Kira et al.	106/109
4,287,103	9/1981	Francis et al.	260/17 R
4,377,977	3/1983	Wurster	109/83
4,476,187	10/1984	Chang	428/325
4,481,177	11/1984	Valyocsik	423/329
4,488,909	12/1984	Galer et al.	106/89
4,622,071	11/1986	Matsuura et al.	106/97
4,673,543	6/1987	Akasaka et al.	264/82
4,799,961	1/1989	Friberg	106/93

FOREIGN PATENT DOCUMENTS

1160945 4/1991 Japan .

Primary Examiner—Christopher A. Fiorilla
Attorney, Agent, or Firm—McAulay Fisher Nissen Goldberg & Kiel, LLP

[57] **ABSTRACT**

A process for preparing calcium silicate articles having a bulk density of 0.3 to 0.9 g/cm^3 including the steps of mixing a major portion of calcium silicate and minor portions of anhydrous calcium aluminosilicate or its analogue, a reinforcing fiber and a polymer binder in water to give an aqueous slurry, molding the slurry into a desired for, and drying the molded slurry at 100°–180° C.

4 Claims, No Drawings